


A01  ArcelorMittal ArcelorMittal Belgium NV ArcelorMittal Gent John Kennedylaan, 51 9042 Gent (België)	A02 CERTIFICATE ----- TEST REPORT ACCORDING EN10204-2.2 OR EQUIVALENT.	A03 200453093 P. 01/01	A09 DISPATCH NOTE 3025535 DATE 11-03-2020	A06.1 CUSTOMER RUSSIA RUSSIA
	A05 AUTHOR OF THE DOCUMENT AM GENT/ QUALITY DEPARTMENT	A08 ORDER NUMBER 50613 DATE	A07 YOUR ORDER NO 4500108085 DATE 16-09-2019	A06.2 DESTINATION RUSSIA RUSSIA
		CONTRACT NO GEOORU2002	YOUR REFERENCES	B06 MARKING NAME SUPPLIER COIL NUMBER STEEL GRADE INK STAMP
		OUR REFERENCES OBC-IN/ICOR		

BO1-BO4 COLD ROLLED COILS, ANNEALED, SKINPASSED, ELECTROGALVANISED, STANDARD = EN10152 (MAY 2009)
 QUALITY DCO6+ZE, 5,0 MICRON / 5,0 MICRON PHOSPHATING (ROHS COMPLIANCE)
 STAND: EN 10131 (2006) NORM.TOL.

B09 ITEM	B10 WIDTH	B11 THICKNESS	REF. CUSTOMER
	MM	MM	
09	1.590	0.70	BC007357

		CHEMICAL ANALYSIS																		
		C70 STEELMAKING PROCESS: LD																		
B09 ITEM	PACK NR	B13 GROSS WEIGHT	B07 COIL NO	B08 CAST N.	C71	C72	C73	C74	C75	C76	C77	C78	C79	C80	C81	C82	C83	C84	C85	
		KG			C	Mn	Si	P	S	N	Al _t	Ti	Cr	Ni	Cu	Nb	B	V	Mo	
					10 ⁻³ %	10 ⁻² %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻⁴ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻³ %	10 ⁻⁴ %	10 ⁻³ %	10 ⁻³ %	
09	865856642	8830	33721743	62558	2	11	2	3	6	15	40	47	11	6	5	0	1	2	1	
	1	8830																		
	1	8830																		

MECHANICAL PROPERTIES
TENSILE TEST

B09 ITEM	PACK NR	CO4	CO2	C11 YIELD	C12 STRENGTH	C13			
				Rp0.2	Rm	A	r	n	
				MPa	MPa	%	10 ⁻²	10 ⁻³	
09	865856642	F	D	136	271	45	260	255	
	1								

REMARKS

TENSILE TEST SPECIMEN LC/LO/BO 120/80/20 MM.
 REFERENCES

BC007357
 VW RUSIA

CO4 CONDITION OF THE SPECIMEN V: AGED F: NON-AGED N: NORMALISED	CO2 DIRECTION SPECIMEN L: OGR S: 45GR D: 9OGR
--	--

GENT 11-03-2020

R. SLOCK
 QUALITY DEPARTMENT



Z01